



Zytel[®] HTN

high performance polyamide resin

PRELIMINARY DATA

Zytel[®] HTNFR52G30BL NC010

Glass Reinforced, Flame Retardant High Performance Polyamide Resin

Zytel[®] HTNFR52G30BL NC010 is a 30% glass reinforced, flame retardant, lubricated high performance polyamide resin that has been developed for connector applications.

Property	Test Method	Units	Value
			DAM
Mechanical			
Tensile Strength	ASTM D 638	MPa (kpsi)	172 (25)
Elongation at Break	ASTM D 638	%	2.2
Flexural Modulus	ASTM D 790	MPa (kpsi)	11400 (1650)
Flexural Strength	ASTM D 790	MPa (kpsi)	240 (34.8)
Izod Impact	ASTM D 256	J/m (ft lb/in)	115 (2.2)
Unnotched Impact	ASTM D 4812	J/m (ft lb/in)	800 (15)
Thermal			
Heat Deflection Temperature	ASTM D 648	°C (°F)	
0.45MPa (66psi)			296 (565)
1.8MPa (264psi)			278 (532)
Flammability			
Rating @ Min. Thickness	UL94		V-0
Min. Thickness Tested	UL94	mm	0.85
Other			
Specific Gravity	ASTM D 792	%	1.62
Mold Shrinkage			
Flow, 1.6mm (0.062in)			0.2
Transverse, 1.6mm (0.062in)		0.9	

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc. Mechanical properties measured at 23°C (73°F) unless otherwise stated.

During molding, use proper protective equipment and adequate ventilation. Avoid exposure to fumes and limit the hold up time and temperature of the resin in the machine. Purge degraded resin carefully with HDPE.

The above data are preliminary and are subject to change as additional data are developed on subsequent lots.

Zytel[®] is a DuPont registered trademark.

980929/000224

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. Caution: Do not use this product in medical applications involving permanent implantation in the human body. For other medical applications see "DuPont Medical Caution Statement", H-51459 or H-50102.

Start with DuPont Engineering Polymers - www.dupont.com/engpolymers

Product Information

Zytel® HTNFR52G30BL NC010

Property	Test Method	Units	Value
			DAM
Processing			
Melt Temperature Range		°C (°F)	325-330 (615-625)
Mold Temperature Range		°C (°F)	60-130 (140-265)
Mold Temperature Optimum		°C (°F)	100 (212)
Drying Time, Dehumidified Dryer		h	6-8
Drying Temperature		°C (°F)	100 (210)
Air Dew Point		°C (°F)	<-20 (<-4)
Processing Moisture Content		%	<0.1

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc.
Mechanical properties measured at 23°C (73°F) unless otherwise stated.

The above data are preliminary and are subject to change as additional data are developed on subsequent lots.

Zytel® is a DuPont registered trademark.

980929/000224

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. Caution: Do not use this product in medical applications involving permanent implantation in the human body. For other medical applications see "DuPont Medical Caution Statement", H-51459 or H-50102.

Start with DuPont Engineering Polymers - www.dupont.com/enggpolymer